

LG Hausys Deco Foil_Hard Coated Foil

[Technical Data]

Test	Methods	Grade/Value Guaranteed by LG
Gloss level	DIN EN 13722:2004	Gloss : 92 ± 2
		Super matt : 6 ± 2
Colour discrepancy	DIN 6174:2007, DIN 6175:2009, According to DIN 5033:2009	Light Colours E= ± 0.5 ,L= ± 0.4 , A= ± 0.3 ,B= ± 0.4
		Dark Colours E= ± 0.8 ,L= ± 0.4 , A= ± 0.4 ,B= ± 0.4
Rub off test	DIN 68861 Part 2	2A
Scratch test	DIN 68861 Part 4	4F (0.47N)
Dry heat	DIN 68861 Part 7	7D
Humid heat	DIN 68861 Part 8	8B
Chemical substance test	DIN68861, T1:2001-04, DIN68930	1B
Sun test 30 H	Grey scale / Colour change according to DIN EN 20105-A02:1994 / EN 15187:2006	5(20hr)
Grille test	DIN EN ISO, 2409-2010	GT 0